



PRODUCT	ALFA	BETA	GAMMA	SIGMA	KAPPA
Materiaal	3-laags spinvliesfolie	3-laags spinvliesfolie	3-laags spinvliesfolie	3-laags spinvliesfolie	3-laags spinvliesfolie
Gewicht	110 gr/m ²	130 gr/m ²	160 gr/m ²	190 gr/m ²	220 gr/m ²
Rolafmeting	1,5 x 50 mtr. (= 75 m ²)	1,5 x 50 mtr. (= 75 m ²)	1,5 x 50 mtr. (= 75 m ²)	1,5 x 50 mtr. (= 75 m ²)	1,5 x 50 mtr. (= 75 m ²)
Waterdichtheid	klasse W1	klasse W1	klasse W1	klasse W1	klasse W1
Waterdamp diffusieweerstand = Sd waarde	0,03 m	0,03 m	0,03 m	0,03 m	0,04 m
Waterdampdoorlatendheid 38° C	ca. 3500 gr / m ² / 24h	ca. 3500 gr / m ² / 24h	ca. 3000 gr / m ² / 24h	ca. 3000 gr / m ² / 24h	ca. 2800 gr / m ² / 24h
Brandwerendheid	klasse E	klasse E	klasse F	klasse F	klasse F
Treksterkte - lengte	220 N / 50 mm	260 N / 50 mm	310 N / 50 mm	380 N / 50 mm	390 N / 50 mm
Treksterkte - breedte	120 N / 50 mm	160 N / 50 mm	210 N / 50 mm	240N / 50 mm	260 N / 50 mm
Scheursterkte - lengte	120 N	140 N	215 N	235 N	290 N
Scheursterkte - breedte	130 N	190 N	250 N	340 N	370 N
Rek bij breuk - lengte	80%	80%	90%	120%	90%
Rek bij breuk - breedte	115%	120%	130%	140%	110%
UV bestendigheid	90 dagen	90 dagen	90 dagen	90 dagen	180 dagen

15 jaar
garantie

PROTECX

Molenkamp 17 - 9473 TP - de Groeve
050-4090773 - info@protecx.nl - www.protecx.nl

EC
normering